Finishing

Shoe Upper

TFL CLIENT DATE **SEPT. 2023** ARTICLE N°7 MEDLAR BU 6085 RECIPE NO.

MATERIAL COW F.G BASED ON WE RECIPE NO.

COLOUR TPX 17 - 1463 TECHNICIAN **Borgia Roberto**

Product	1	2	3	4	5	6	Procedure
						ļ	
RODA® Polipearl Iride Blue	50					<u> </u>	1) 3X SPRAY
Water	_ <u>i</u>	150	400			<u>i</u>	
RODA® Pur 5101/N	900					<u> </u>	2) 2X SPRAY
RODA® Lac WG/4	L	50			L	<u> </u>	
Water						<u> </u>	3) 2 or 3X SPRAY
RODA® Feel KTA 950		10				<u> </u>	BRUSH OFF TO EFFECT
RODA® Feel KTA 944		10				<u> </u>	KISS PLATE 100°C
RODA® Lite 07 MIX	50		60				
RODA® Lac 103 dull			250				
RODA® Pur 5427/N			150				
RODA® Wax 2014/N			80				
						Ī	
						Ī	
						1	
	i i					Ī	T
	<u> </u>		!			<u> </u>	
	<u> </u>					<u> </u>	<u> </u>
	· † · · · · · · ·					†	!
						†	
						 	
						†	
						†	I I
						 	
		L	<u> </u>		L		<u> </u>
						 	
			ļi			†	I
]
					ļ	<u> </u>	! !
						 	
				_	-	-	
Total	1000	220	940	0	0	0	

Comments:

RODA* is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application reccomendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products fire outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.