

# Finishing Shoe Upper



CLIENT **TFL**  
 ARTICLE **N°8 GLORY**  
 MATERIAL **LAMB SKIN**  
 COLOUR **TPX 15-1263**

RECIPE NO.  
 BASED ON WE RECIPE NO.  
 DATE:  
 TECHNIC:

**BU 6079**  
**Sept. 23**  
**TIRELLI/GIAQUINTO**

Product	1	2	3	4	5	6	Procedure
RODA® Base AF-B/N	100						1) 2X SPRAY
WATER	300	700	500				ROTOPRESS 100°C-50 ATM
RODA® Casi MIX	20	100					
RODA® Wax MONO		50					2) 8X SPRAY
RODA® Wax 1423		30					
RODA® Pur EP 19/F		70					3) 2X SPRAY
BAYDERM® Bottom 10 UD		30					IRON 100°C - 50 ATM
RODA® Cryl NP 87		50					
RODA® Cryl 744		50					
RODA® Pur 5329 Conc.		20					
RODA® Feel S 2075		4					
RODA® Link PAX		3	8				
RODA® Fix 5188/N Gloss			320				
RODA® Fix 6271/B			80				
RODA® Bind TLC 327			20				
ROSILK™ 2229			10				
<b>Total</b>	<b>420</b>	<b>1107</b>	<b>938</b>	<b>0</b>	<b>0</b>	<b>0</b>	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.