

**Wet End - Process Formulation (RETANNING)**



<b>ARTICLE : CREAM</b>		<b>Date:</b>	30-Jun-2023
		<b>Technician:</b>	ROMANO GIUSEPPE
<b>Company:</b>	TFL	<b>Trial - N°:</b>	
<b>Type of Leather:</b>	Shoe Upper & Leather Goods	<b>Color:</b>	
<b>Aim of Trial:</b>		<b>Piece count:</b>	25
<b>Project - N°:</b>		<b>Substance:</b>	1,10 mm
<b>Material:</b>	LAMBS CHINA	<b>Weight:</b>	18,000 kg
<b>% refer to:</b>	shaved weight	<b>Drum - N°:</b>	

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		150,00		WATER	50			
		2,00		BORRON SE				
		1,00		DERMASCAL F				
		1,00		BORORN Z				
		0,50		OXALIC ACID			90	DRAIN- WASH
		100,00		WATER	40			
		0,30		FORMIC ACID 85%			15	PH=3,2
		4,00		TANNESCO HN GRAN			30	
		2,50		CORIPOL SLG			30	
		4,00		BLANCOL AC			45	
		4,00		X CROME FD			60	
		4,00		TANNESCO FC			180	OVER NIGHT
								IN THE MORNIG
								DRAIN- WASH
		100,00		WATER	40			
		3,00		SELLASOL NG GRAN			20	
		1,50		CROMENO BF			30	PH=5,8
		3,00		RETINGAN R7			40	DRAIN- WASH
		80,00		WATER	50			
		3,00		RETINGAN R12			40	
		3,00		SELLASOL PR 01			30	
		4,00		LEVOTAN L			20	
		4,00		LUBRITAN SP-E			20	
		100,00		WATER	60			
		4,00		MAGNOPAL IPF				
		3,00		CORIPOL GF				
		3,00		CORIPOL MK				
		2,00		CORIPOL SV				
		2,00		CORIPOL A				
		1,00		BORORN SAF			60	
		6,00		SELLASOL HH-F GRAN				
		12,00		TANIGAN MB-O LIQ			45	
		3,00		MAGNOPAL PGN				
		3,00		MAGNOPAL RHN			40	
		3,00		FORMIC ACID 85%			3X10+60	DRAIN- WASH

**Mechanical Operation:**

HORSE UP OVERNIGHT ,HANG TO DRY

**Process Information:**

**Running Time:**

13 hrs 15 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.  
Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application..