Wet End - Process Formulation (RETAN)

TFL

N°27 STRING WET END.	xlsx	Date:	3-Jul-2023	
		Technician:	Grosch	
Company:		Score:	Select Score	
Type of Leather:	Select Article	Trial - N°:	G 921	
Aim of Trial:	27 - STRING - Nubuck hidro stampato	Color:		
-	· ·	Piece count:	6/2	
Project - N°:		Substance:	1,3/1,5	
Material:	WET-BLUE sh	Weight:	20,500 kg	
% refer to:	wet-blue SH	Drum - N°:		

Operation	Add	%	Weight	Product	Temp.	Dilution	Time	Control
			in kg		in ℃	(1 : x)	in min	
		200,00	41,000	Water	35			
		0,30	0,062	Formic Acid		10	20	pH:3,2
Drain								
		100,00	20,500		35			
	+	2,00		TANIGAN PAK				
		2,00		Sodiium Formate			30	
	+	0,80		Sodium Bicarbonate			30	
	+	1,00		MAGNOPAL DP		3	10	
	+	2,00	0,410	Levotan PS		3	90	pH; 5,0/5,5
Drain								
		200,00	41,000	Water	30		10	
Drain								
		50,00	10,250		30			
		6,00	1,230	MAGNOPAL PGN			30	
	+	15,00		TANIGAN MB-O		1		
		5,00		RETINGAN Pure RS				
		2,00		BAYKANOL TF-2N C01			20	
	+	1,50		Sellasol TN Gran				
		4,00		BAYGENAL GREY L-NG				
		0,50		SELLA SET BROWN M			90	•
	+	100,00	20,500	Water	50		10	
	+	2,00	0,410	Leukotan 1093		3	20	
		10.00	2.050	LEVOTANI DE		-	60	
	+	10,00	2,050	LEVOTAN PS		4	60	
		1.00	0.205	Farmeia Asid		10	20	
	+	1,00 1,00		Formic Acid Formic Acid		10 10	20 20	
	+	1,00		Formic Acid		10		pH: 3,4/3,6
Drain		1,30	0,207	FOI THIC ACIU		10	20	рп. 3,4/3,0
Dialli		200,00	41,000	Water	30			
		0,50		Borron WP	30		15	
Drain		0,30	0,103	BOTTOTT WF			13	
Diani		150,00	30,750	Water	30			
	+	3,00		chrome 33	30		90	
Drain	+ '-	3,00	0,013	difference 55			30	
Diani		200,00	41,000	Water	30		10	
Drain		200,00	41,000	VVater	30		10	
		200,00	41,000	Water	30		10	
Drain		200,00	,		30		10	
Aechanical Operation:				l	Process In	formation:		1
Horse-un set-out vacuum dry 180sec@45°C hang dry stake			aka	•				

Horse-up, set-out, vacuum dry 180sec@45°C, hang dry, stake

Running Time: 10 hrs 05 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or

application.